

PROVINCIAL RUBBER LTD



Unit 6 Riverside Business Park
St Annes Road, St Annes
Bristol
BS4 4ED
0117 9541117

Neoprene Rubber Cord

70 Shore

Material Description : 70 IRHD Neoprene Compound

Properties	Spec	Results	Unit
Physical Properties :			
Durometer Hardness	68-78	74	IRHD
Tensile Strength		97	Mpa
Elongation at Break		219	%
Compression Set, Max. 22h at 100°C	ASTM D395 Test Method B	46.2	%

The information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check and test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.