

Grey Polyether Polyurethane Foam

Typical Physical Properties

Physical properties are measured using test methods described in the BS4443 series and BS EN ISO 845:1995

Nominal piece density range	23.8 – 26.3 kg/m ³
Nominal hardness range	120-160 N
Nominal tensile strength	50 kPa min
Nominal elongation at break	90% min.
UV Stability	Poor

Foam Classification (BS3379)	
Nominal Classification	A

Flammability Characteristics

Complies with the requirements of Schedule 1, Part 1, The Furniture and Furnishing (Fire)(Safety) Amended Regulations 1989.

Under Writers Laboratories – UL94 HF1 Classification

The information and our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty. This also applies where proprietary rights are involved. Our advice does not release you from the obligations to check and test our products as to their suitability for the intended use. The storage, application and use of our products are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with our General Conditions of Sale. The information contained within this data sheet is subject to change without notice.